

LOCTITE®



LOCTITE® 3D IND5714™

Elastomer
Gray

LOCTITE®
Henkel Corporation
loctite3dp@henkel.com





IND5714™ ELASTOMER



LOCTITE 3D IND5714™

LOCTITE 3D IND5714 is an industrial elastomer with a low hazard labelling, a low shore A hardness and excellent repetitive strain resistance.

The properties of LOCTITE 3D IND5714, including the high rebound characteristics, excellent elongation at break and low modulus, makes it an ideal choice for cushioning and dampening applications in a wide range of industries.

LOCTITE 3D IND5714 is compatible with a broad range of DLP and LCD machines.



Benefits:

- Excellent H&S rating and TPO-Free
- Improved processing
- High rebound and excellent compression characteristics
- Soft feel and high elongation




Ideal for:

- Cushioning and dampening applications such as shock absorbers, gaskets and seals
- Sporting and consumer goods
- Soft robotics (grippers, prosthetics)



Markets:

Industry	Consumer Goods	Automotive





PROPERTIES

Mechanical Properties	Measure	Method	Green	Post Processed
Young's Modulus	MPa	ASTM D638	-	4.1 – 4.9 [10]
Tensile Stress at Break	MPa	ASTM D638	-	1.4 [10]
Elongation at Break	%	ASTM D638	-	130 – 143 [10]
Stress at 50% Strain	MPa	ASTM D412	0.7 [9]	1.2 [9]
Stress at 100% Strain	MPa	ASTM D412	1.0 [9]	1.7 [9]
Stress at 150% Strain	MPa	ASTM D412	1.3 [9]	2.3 [9]
Stress at Break	MPa	ASTM D412	2.0 – 2.4 [9]	2.9 [9]
Strain at Break	%	ASTM D412	228 – 261 [9]	191 – 195 [9]
Tear Strength	kN/m	ASTM D624	-	8.4 – 9.4 [8]
Energy Return	%	Internal	-	55 – 63 [4]
Compression Set (22°C/24hr)	%	D395-B	-	8 – 11 [3]
Compression Set (70°C/24hr)	%	D395-B	-	25 – 32 [3]
Shore Hardness (5s)	A	ASTM D2240	-	53 [2]
Other Properties				
Solid Density (Cured)	g/cm ³	ASTM D792	-	1.04 [1]
Water Absorption (24hr)	%	ASTM D570	-	3.5 [5]
Water Absorption (72hr)	%	ASTM D570	-	5.0 [5]
Water Absorption (168hr)	%	ASTM D570	-	5.3 [5]
Biocompatibility				
Cytotoxicity		ISO10993-5		Pending
Liquid Properties				
Viscosity at 25°C (77°F)	cP	ASTM D7867		2700 [6]
Liquid Density	g/cm ³	ASTM D1475		1.01 [7]

Test parameters:

"All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours." ASTM Methods: D638 Type IV, 50 mm/min, D412 Type C, 500 mm/min, D570 0.125" x 2" Disc 24hr@ 25°C, D2240, Type "A" (5 seconds), D7867, D1475

*The biological assessment has been performed based on the in vitro method according to ISO10993-23

Internal Data Sources:

[1] FOR512549, [2] FOR505649, [3] FOR506506, [4] FOR506522, [5] FOR504267, [6] FOR481424, [7] FOR459194, [8] FOR491459, [9] FOR491455, [10] FOR516571





WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

PRINTER SETTINGS

LOCTITE 3D IND5714 GY is formulated to print optimally on LCD and DLP printers. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 35°C
- Intensity: 3 mW/cm² to 7 mW/cm²

Settings: 385 nm at 5 mW/cm ²	Measure	Method	Value
Layer Thickness	µm	Internal	100
Burn-in Region	s	Internal	40
Transition Region	s	Internal	25
Model Region	s	Internal	10

Settings: 385 nm at 5 mW/cm ²	Measure	Method	Value
E _C	mJ/cm ²	Internal	16.12 ^[1]
D _p	mm	Internal	0.12 ^[1]

Settings: 385 nm at 5 mW/cm ²	Measure	Method	Exposure time
D _C = 50µm	s	Internal	5*
D _C = 100µm	s	Internal	7*

Test parameters:
Exposure times are calculated without a safety factor

Internal Data Sources:
[1] FOR459191





IND5714™
ELASTOMER
GRAY



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

CLEANING

LOCTITE 3D IND 5714 GY requires post processing to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

Post Process Step	Agent	Method	Duration	Interval	Additional Info
Cleaning #1	IPA	Sonic	2 min	1-2	Allow parts to dry between intervals
Dry	n.a.	Compressed air	30 s	1	Use compressed air between intervals
Wait before post curing	n.a.	Ambient	60 min	1	Room temperature

POST CURING

LOCTITE 3D IND5714 GY requires post curing to achieve specified properties. It is recommended to use a wide spectrum lamp post UV cure device.

UV Curing Unit	UV Source	Intensity	Cure time Per side	Additional Settings (Shelf, Output Energy)
Loctite UVALOC 1000	Mercury Arc Bulb (broad spectrum)	30 mW/cm ² at 365nm	10 min	500 W, 1 st shelf from bottom

STORAGE

Store **LOCTITE 3D IND5714 GY** in the unopened container in a dry location. Optimal Storage: 8°C to 30°C. Storage below 8°C or above 30°C can adversely affect product properties. Material removed from containers may be contaminated during use. For this reason, filter used resin with 190µm mesh filter before placing back into proper storage container.









AGEING AND ENVIRONMENTAL EFFECTS – HEAT AGEING

LOCTITE 3D IND5714 GY was heat aged without load according to ASTM D3045. Test samples were exposed for a defined time at 50°C and conditioned for 24 hours at 22°C before mechanical testing. Control samples were stored at a constant 22°C. All samples were printed in the same print job using a validated workflow. Mechanical testing was conducted according to ASTM D412 at standard lab conditions (22°C). "0 weeks" represents non-aged samples stored at 22°C and tested 24 hours after post-processing.

Based on temperature dependence of reaction rates a test time of 6 weeks at 50°C can be interpreted as approximately 12 months at ambient temperature.



Test parameters:
ASTM D412: Type Die C, Pull speed: 500 mm/min, 22°C

Internal Data Sources:
[FOR511094](#), [FOR511097](#)







IND5714™
ELASTOMER
GRAY



THERMAL INFLUENCE ON MECHANICAL PROPERTIES

LOCTITE 3D IND5714 GY has been tested according to ASTM D412 at varied environmental temperatures, from -40°C to 100°C. All samples were printed in the same print job using a validated workflow. Mechanical testing was conducted according to ASTM D412. Before each test series samples were conditioned for 60 minutes at the specific test temperature.



Test parameters:
ASTM D412: Type Die C, Pull speed: 500 mm/min



Internal Data Sources:
[FOR548431](#), [FOR544068](#)





AGEING AND ENVIRONMENTAL EFFECTS – CHEMICAL RESISTANCE (1/2)

LOCTITE 3D IND5714 GY has been tested after chemical ageing according to ASTM D543. The influence of chemicals was tested by measuring mechanical properties after different test times (Immersion test for 24 and 168 hours). Exposed samples were stored in containers and fully immersed in different chemicals. Samples were stirred every 24 hours using a shaker. After removal, exposed samples were washed and conditioned for 24 hours at 22°C before mechanical testing. All samples were printed using a validated workflow. Mechanical testing was conducted according to ASTM D412 at standard lab conditions (22°C). "100%" represents non-aged samples stored at 22°C and tested 24 hours after post-processing.



Test parameters:

ASTM D412: Type Die C, Pull speed: 500 mm/min, 22°C

ASTM D543: Samples immersed in different chemicals were stored at 22°C. Samples immersed in Motor Oil were stored at 50°C.

Properties of media used: pH(HCl, 10%) = 1; pH(NaOH, 10%) = 14; pH(NaClO, 5%) = 13

Internal Data Sources:

[FOR537139](#), [FOR537140](#), [FOR538045](#), [FOR538046](#), [FOR559225](#), [FOR559226](#), [FOR559229](#)






IND5714™
ELASTOMER
GRAY



AGEING AND ENVIRONMENTAL EFFECTS – CHEMICAL RESISTANCE (2/2)

LOCTITE 3D IND475 BK has been tested after chemical ageing according to ASTM D543. The influence of chemicals was tested by measuring the mass change after different test times (Immersion test for 24 and 168 hours). Exposed samples were stored in containers and fully immersed in different chemicals. Samples were stirred every 24 hours using a shaker. After removal exposed samples were washed, dried and immediately weighed. All samples were printed using a validated workflow. "100%" represents the initial weight 24 hours after post-processing.



Test parameters:

ASTM D543: Samples immersed in different chemicals were stored at 22°C. Samples immersed in Motor Oil were stored at 50°C.
Properties of media used: pH(HCl, 10%) = 1; pH(NaOH, 10%) = 14; pH(NaClO, 5%) = 13

Internal Data Sources:

[FOR538060](#), [FOR538066](#), [FOR538091](#), [FOR538092](#), [FOR559230](#), [FOR559231](#), [FOR559232](#)





IND5714™
ELASTOMER



NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.





FIND OUT MORE AT
LOCTITEAM.COM